

termolac®

High quality polyester powder paint for roll products

Technical data sheet

TEST	termolac®
Pretreatment SHEETS	-Trivalent Chromium transparent green coloured -Possibility Chromium-free
Pretreatment COILS	-Phosphocromatized film with Green pigmentation -Possibility Chromium-free
Powder characteristics	High quality polyester for external use
Aspect	Any defect from 1 meter distance
Gloss 60° [ISO 2813] [ECCA T2]	0-30±5 / 31-70±5 / 71-100±10
Coating thickness [ISO 2360] [ECCA T1]	70±10µ average
Adherence [ISO 2409] [ECCA T6]	GT0
Buchholz indentation [ISO 2815] [ECCA T12]	90
Cupping test [ISO 1520]	6-12mm*
Bending test (bending radius) [ECCA T7]	Bending radius equals zero=0T*
Impact test (without cracking) [ECCA T5]	10Nm
Corrosion resistance [ISO 9227]	1000 hours without corrosion **
Quality certificate	Qualicoil® (with each order)
Warranty	Up to 10 year depending on the alloy, color and location of the building

*Depending on the alloy/temple/thickness and selected colour

**Depending on alloy/rolling of metal

